specimen contains a network sheet, in particular a net shown in Fig. 1, La and Lb are desirably measured as follows. A 100mm long along the direction perpendicular to the fiber orientation and 100 mm wide specimen was cut out of the bulky sheet. The length of the specimen La (mm) in the longitudinal direction thereof was measured. Then the network sheet was cut by a cutter at the points between the intersection of the network sheet along the direction perpendicular to the fiber orientation (attention was paid so as not to cut the fibers). The specimen was then cut into a strip having 15 mm width along the fiber orientation. The weight was put on the strip, and then the measurement of the length Lb was carried out.